



Integrating Structure with Power in Battery Materials

by James F. Snyder, Robert H. Carter, and Eric D. Wetzel

ARL-RP-190

September 2007

*A reprint from the Proceedings of the 2004 Army Science Conference,
Orlando, Florida, 29 November – 2 December 2004.*

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5069

ARL-RP-190**September 2007**

Integrating Structure with Power in Battery Materials

James F. Snyder, Robert H. Carter, and Eric D. Wetzel

U.S. Army Research Laboratory

Weapons and Materials Research Directorate

A reprint from the *Proceedings of the 2004 Army Science Conference*,
Orlando, Florida, 29 November – 2 December 2004.

REPORT DOCUMENTATION PAGE				<i>Form Approved</i> OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) September 2007		2. REPORT TYPE Reprint		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE Integrating Structure with Power in Battery Materials				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) James F. Snyder, Robert H. Carter, and Eric D. Wetzel				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRD-ARL-WM-MA Weapons and Materials Research Directorate, Aberdeen Proving Ground, MD, 21005-5069.				8. PERFORMING ORGANIZATION REPORT NUMBER ARL-RP-190	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory 2800 Powder Mill Road Adelphi, MD 20783-1197				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S) ARL-RP-190	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT This report is a reprint from the <i>Proceedings of the 2004 Army Science Conference</i> at Orlando, Florida, in 2004. We have developed a multifunctional material concept that combines structural performance with power generation. Such devices would replace inert structural components in U.S. Army systems, such as a ground vehicle body or a soldier's helmet, and simultaneously provide supplementary power for light load applications. The emphasis of our research is two-fold. We are developing structural polymer electrolytes that exhibit desirable ion conductivity, and we are researching augmentation of overall mechanical properties in polymer based power generating devices.					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT SAR	18. NUMBER OF PAGES 8	19a. NAME OF RESPONSIBLE PERSON James F. Snyder
a. REPORT U	b. ABSTRACT U	c. THIS PAGE U			19b. TELEPHONE NUMBER (Include area code) (410) 306-0842

INTEGRATING STRUCTURE WITH POWER IN BATTERY MATERIALS

James F. Snyder*, Robert H. Carter, and Eric D. Wetzel
Army Research Laboratory, Weapons and Materials Research Directorate
Aberdeen Proving Ground, MD 21005

1. Abstract

We have developed a multifunctional material concept that combines structural performance with power generation. Such devices would replace inert structural components in U.S. Army systems, such as a ground vehicle body or a soldier's helmet, and simultaneously provide supplementary power for light load applications. The emphasis of our research is two-fold. We are developing structural polymer electrolytes that exhibit desirable ion conductivity, and we are researching augmentation of overall mechanical properties in polymer based power generating devices.

2. Background

Many Army applications require lightweight structural materials. In addition, more weight efficient power generating devices are needed to support the increasing integration of electronic technology into military systems. Current generation batteries add significant bulk and weight to the overall load of the soldier. Much of the remaining load is comprised of inert constituents that provide only structural functionality. Lightweight supplemental battery devices that are seamlessly integrated into existing structural components, simultaneously providing power and carrying static loads, would reduce dependence on traditional batteries and make the Future Force Warrior more agile and survivable. In order to develop such a multifunctional battery, the electrolyte material must be optimized for both the electrochemical performance and the structural properties. Ion conductive polymers are an ideal medium since they can be modified to exhibit a range of mechanical properties and can be cast into thin films while maintaining acceptable limits of ion diffusion.

3. Toughened Electrolytes

3.1 Approach

We are currently exploring two primary routes to enhance polymer electrolyte stiffness and toughness. The first method concentrates on the polymer chemistry, and specifically on developing thermoset resins (Vondrak et al., 1999). Thermoset resins may be

synthesized from monomers with a wide range of functionality and often provide for convenient handling prior to cure. We have chosen to focus our study on resins that include oligo (oxyethylene) units owing to the known ion conductive properties of poly (ethylene oxide), PEO, and the ease with which lithium salts may be dissolved into PEO oligomers. The desired balance between mechanical and electrochemical properties has led us to research partially crosslinked polymer electrolyte matrices that combine monofunctional and difunctional resin monomers, as well as interpenetrating networks of difunctional resins and linear PEO. Table 1 lists some of the polymer materials currently under scrutiny. Ethoxylated bisphenol-A diacrylates are considered as a crosslinking agent owing to the variable number of ion-coordinating ethylene oxide units, indicated in parentheses, which are evenly distributed on either side of the central rigid bisphenol unit. Lithium trifluoromethane-sulfonate (triflate) is used as the lithium salt owing in part to its thermal and electrochemical stability.

The second route of polymer electrolyte development utilizes the reinforcing properties of ceramic fillers and fibers and is also summarized on Table 1. Ceramic fillers have been demonstrated to boost the mechanical and interfacial properties of polymer electrolytes as well as improve the conductivity, the latter owing in part to the plasticizing effect of small particles (Scrosati et al., 2001). Much less attention has been devoted to optimizing the combined effects on structure and ion diffusion through the addition of electrically resistive fibers, although nanoscale alumina whiskers have been shown to have a positive effect on mechanical and electrochemical properties while also preventing microscale cracks (Wen et al., 2002).

Testing of the materials represented by Table 1 involves quantifying the ionic conductivity and mechanical properties of each sample. Indentation techniques have been chosen as a quick test to give a qualitative measurement of the elastic modulus of the material. The samples with the best combination of stiffness and lithium ion conductivity are downselected and subjected to dynamic mechanical analysis (DMA) to give a more quantitative measurement of the elastic properties.

Table 1.

Crosslinking Agent (Diacrylate)	PEO/PEG Matrix		Salt	Filler Reinforcement	
	Comb (Monoacrylate)	Linear		Fiber	Particle
PEG 600	PEO 350 Acrylate	PEO 200k	LiOTf	Glass, Silica	Silica
Ethox. (30) Bis-A	PEO 550 Acrylate	PEO 1,000k		Alumina	Alumina

3.2 Experimental

Chemicals were handled in a glove box under dry nitrogen. Lithium triflate was purchased from Sigma Aldrich Chemical Company and dried for 12 hours under vacuum at 180 °C. Monomer samples, received from Sartomer Company, Inc., were mixed thoroughly with the appropriate amount of lithium triflate in a glass vial. Dissolution of the salt was aided by briefly heating the vial up to 80 °C. 1.5 wt% initiator (Trigonox) and 1 wt% dimethylaniline were stirred into the vial at room temperature. The resulting solution was poured into a pellet shaped rubber mold and heated under nitrogen to 80 °C for 12 hours, followed by 100 °C for 1 hour, and then allowed to cool to room temperature. The cured pellets were painted on both sides with quick drying silver paint and further heated to 80 °C under vacuum for 12 hours to remove residual solvent and water.


Conductivity values were calculated from data collected through impedance spectroscopy. It was found that conductivity was optimized at 6-9 wt% salt for the resins in Table 1. Ethoxalated (30) bisphenol-A has the highest conductivity of Sartomer's difunctional resins, with a maximum of 2×10^{-6} S/cm at 9 wt% salt. Conductivity values 20 times higher were measured for PEG 550 acrylate, which is very soft. Blends of monofunctional and difunctional monomers are being developed to create materials with both high conductivity and robust mechanical properties. Elastic modulus values for initial blend formulations, as measured by indentation, have been 0.1-0.01 GPa.

Limited studies have also been conducted using silica particles as additives. Addition of 10% silica has been found to have a five-fold increase in modulus with an accompanying 75% reduction in conductivity. Addition of 20% silica has a ten-fold increase in modulus. Further experimentation is underway.

4. Battery Design

In addition to developing electrolyte materials, our research focuses on improving the overall structural properties in power source devices. In particular, we are designing configurations to optimize the overall structural efficiency of battery devices that may replace inert structural components. Figure 1 shows a generic representation of how this might be accomplished using a

carbon fiber anode. In this structure, the polymer electrolyte serves as the matrix phase in the structural composite. This design requires the electrolyte to possess both good mechanical properties, to enable load transfer to the reinforcing fibers and metal mesh, and good ionic conductivity, for acceptable power density. The carbon fiber reinforcement serves multiple purposes. As an anode material, it intercalates the lithium ions and conducts electrons out of the cell. As a reinforcement material, the high stiffness and strength of the carbon fibers greatly enhances the structural capacity of the composite. A layer of glass fabric is also included in the design, to ensure electrical isolation of the anode and cathode, improve mechanical properties, and possibly enhance the ion conductivity of the electrolyte.

**Figure 1.**

5. References

- [1] Vondrak, J., Sedlarikova, M., Reiter, J., and Hodal T., 1999: Polymer gel electrolytes for electrochromic devices, *Electrochim. Acta*, **44**, 3067-3073.
- [2] Scrosati, B., Croce, F. and Panero, S., 2001: Progress in lithium polymer battery R&D, *J. Power Sources*, **100** (1-2), 93-100.
- [3] Wen, Z., Wu, M., Itoh, T., Kubo, M., Lin, Z., and Yamamoto, O., 2002: Effects of alumina whisker in (PEO)(8)-LiClO₄-based composite polymer electrolytes, *Solid State Ionics*, **148**, 185-191.

6. Acknowledgements

We would like to thank Dr. Kang Xu and Dr. Richard Jow of the Battery Team, SEDD, ARL, for their assistance with the conductivity measurements.

Distribution List

ADMNSTR 1 elec
DEFNS TECHL INFO CTR
DTIC OCP (ELECTRONIC COPY)
8725 JOHN J KINGMAN RD STE 0944
FT BELVOIR VA 22060-6218

US ARMY RSRCH LAB 6
IMNE ALC IMS MAIL & RECORDS MGMT
AMSRD ARL D J M MILLER
AMSRD ARL CI OK TL TECHL LIB (2 COPIES)
AMSRD ARL CI OK T TECHL PUB (2 COPIES)
2800 POWDER MILL ROAD
ADELPHI MD 20783-1197

US ARMY RESEARCH LAB 1
AMSRD CI OK TP TECHL LIB
ATTN T LANDFRIED
APG MD 21005

US ARMY RESEARCH LAB 2
AMSRD ARL WM MA J SNYDER
AMSRD ARL WM MB R CARTER
BUILDING 4600
APG MD 21005-5069

TOTAL 10 (1 Electronic, 9 HCs)

INTENTIONALLY LEFT BLANK.